


















































































# CHEMICAL RESISTANCE COMPATIBILITY GUIDE

Media	Immersion Days	Temp	% Strain	VALOX 357 Resin (UL94 V0 Rated)	
<b>Acids</b>					
10% Hydrochloric Acid	30	77°F	0	100	
	90			100	
10% Sulphuric Acid	30	77°F	0	100	
	90			100	
30% Sulphuric Acid	30	77°F	0	100	
	90			100	
	30	140°F	0	100	
	90			100	
10% Acetic Acid	30	77°F	0	100	
	90			100	
<b>Bases</b>					
5% Potassium Hydroxide	30	77°F	0	100	
	90			97	
10% Sodium Hydroxide	30	77°F	0	100	
	90			100	
10% Ammonium Hydroxide	30	77°F	0	63	
	90			31	
<b>Organic Solvents</b>					
Ethyl Alcohol	30	77°F	0	98	
	90			97	
Methyl Alcohol	30	77°F	0	80	
	90			68	
Isopropyl Alcohol	30	77°F	0	100	
	90			100	
IPA – Water (50/50)	30	77°F	0	98	
	90			100	
Heptane	30	77°F	0	100	
	90			100	
Acetate	30	77°F	0	32	
	90			34	
<b>Methylethylketone</b>					
Ethyl Acetate	30	77°F	0	33	
	90			36	
Methylene Chloride	30	77°F	0	29	
	90			34	
Ethylene Glycol	30	77°F	0	21	
	90			24	
	30	77°F	0	100	
	90			100	
<b>Automotive Related Environments</b>					
Motor Oil	30	77°F	0	100	
	90			100	
	30	250°F	0	100	
	90			86	
<b>Transmission Fluid</b>					
	30	77°F	0	100	
	90			100	
	30	250°F	0	72	
	90			36	

# CHEMICAL RESISTANCE COMPATIBILITY GUIDE

Media	Immersion Days	Temp	% Strain	VALOX 357 Resin (UL94 V0 Rated)
Power Steering Fluid	30	77°F	0	100 
	90			100 
	30	140°F		100 
	90			100 
Brake Fluid	30	77°F	0	100 
	90			93 
	30	140°F		70 
	90			46 
Regular Gasoline	30	77°F	0	100 
	90			100 
	30	140°F		100 
	90			92 
Premium Gasoline	30	77°F	0	100 
	90			98 
	30	140°F		81 
	90			67 
Unloaded Gasoline	30	77°F	0	100 
	90			100 
	30	140°F		95 
	90			82 
Gasohol (90/10)	30	77°F	0	96 
	90			86 
	30	140°F		51 
	90			42 
Diesel Fuel	30	77°F	0	100 
	90			100 
	30	140°F		100 
	90			100 
<b>Salts</b>				
10% Zinc Chloride	30	77°F	0	100 
	90			99 
10% Calcium Chloride	30	77°F	0	100 
	90			98 
5% Sodium Chloride	30	77°F	0	99 
	90			99 

Compatibility Rating Basis		
Colour Rating	Elongation (% Retention)	Tensile (% Retention)
 MARGINAL	65%-79%	80%-89%
 NOT COMPATIBLE	<=64% OR >=140%	<=79
 COMPATIBLE	80%-139%	>=90%

## LIABILITY STATEMENT

All care and diligence has been used in processing, analysing and extracting the information contained in this document. Rteck Pacific Ltd accepts no liability for any errors which may inadvertently appear in the document. Rteck Pacific Ltd shall not be liable for any loss or damages suffered by customers upon the use directly or indirectly of information supplied herein.